



<b>Pigment Name</b>	Prussian Blue
<b>C.I. Constitution No.</b>	77510 & 77520
<b>C.I. Pigment</b>	Blue 27
<b>Physical Appearance</b>	Reddish Blue
<b>Fineness</b>	Min. 99.5% passes through 240 Mesh
<b>Volatile Matter</b>	Not more than 2 %
<b>Oil Absorption</b>	90
<b>Colour</b>	Bronze Blue
<b>Tone</b>	Redder
<b>pH Value</b>	3.5 ± 1.00
<b>Acid Resistance</b>	Excellent
<b>Alkali Resistance</b>	Very Poor
<b>Specific Gravity</b>	1.7 - 1.8
<b>Bulk Density</b>	0.4 - 0.45
<b>Light Fastness</b>	Full Tone 6 - 7
<b>Tint Tone 4</b>	[ TiO <sub>2</sub> 1 : 20 ]

### MAJOR APPLICATIONS

Paints & Marine Paints, Printing Ink, Carbon Paper & Typewriter Ribbons, Poster Colours, Construction Chemicals.

**Disclaimer:** "The information given herein & otherwise supplied to users is based on our general findings. Because of the factors that are beyond our knowledge & control, which can affect the use of products, we accept no liability regarding the suitability, if use of the product for any particular purpose."